## **CLAIMS**

What is claimed is:

1. A method for reconditioning a lithium ion battery having reduced capacity, comprising the steps of:

providing a lithium ion battery including a negative electrode, a positive electrode, a nonconductive separator disposed between the negative electrode and the positive electrode, and a source of lithium and an electrolytic solution hermetically sealed in a container, and further including a negative terminal connected to the negative electrode and a positive terminal connected to the positive electrode extending through a face of the container to provide external connections;

slowly discharging the lithium ion battery to a predetermined voltage sufficiently high so as not to damage the battery cells and at a rate sufficiently low to redistribute lithium ions in the negative electrode while substantially completely discharging the battery; then

providing a power source;

connecting the power source to the negative terminal and the positive terminal of the battery;

providing power to the battery from the power source to recharge the lithium ion battery so as to substantially uniformly redistribute the lithium ions in the positive electrode;

wherein the capacity of the battery is substantially restored

2. A method for reconditioning a lithium ion battery having reduced capacity, comprising the steps of:

providing a power source;

providing a lithium ion battery including a negative electrode, a positive electrode, a nonconductive separator disposed between the negative electrode and the positive electrode, and a source of lithium and an electrolytic solution hermetically sealed in a container, and further including a negative terminal connected to the negative electrode and a

positive terminal connected to the positive electrode extending through a face of the container to provide external connections;

connecting the power source to the negative terminal and the positive terminal of the battery;

slowly discharging the lithium ion battery to a predetermined voltage sufficiently high so as not to damage the battery cells and at a rate sufficiently low to redistribute lithium at the negative electrode while substantially completely discharging the battery; and

providing power to the battery from the power source to recharge the lithium ion battery so as to substantially uniformly redistribute the lithium in the positive electrode;

wherein the capacity of the battery is substantially restored.

- 3. The method of claim 2 wherein the step of providing a lithium ion battery includes providing a metal oxide-based positive electrode.
- 4. The method of claim 3 wherein the step of providing a metal oxide-based positive electrode includes providing a nickel oxide-based positive electrode.
- 5. The method of claim 4 wherein the step of slowly discharging the battery includes slowly discharging the battery at a voltage above at least about 1.6 volts.
- 6. The method of claim 3 wherein the step of providing a metal oxide-based positive electrode includes providing a cobalt oxide-based positive electrode.
- 7. The method of claim 6 wherein the step of slowly discharging the battery includes slowly discharging the battery at a voltage above at least about 0.5 volts.
- 8. The method of claim 2 wherein the step of providing a lithium ion battery includes providing a carbonaceous negative electrode.
- 9. The method of claim 2 wherein the step of providing a lithium ion battery includes providing a battery having an electrolytic solution comprising LiPF<sub>6</sub>, phosphor hexachloride and organic carbonate.
- 10. The method of claim 2 wherein the step of slowly discharging the lithium ion battery further includes the step of reducing the capacity of the battery in stages to

a capacity value of C/n to the predetermined voltage, where C is the rated capacity of the battery.

- 11. The method of claim 10 wherein the step of reducing the capacity of the battery is performed in a plurality of stages.
- 12. The method of claim 11 wherein the plurality of stages is performed at a predetermined temperature, a number of stages in the plurality of stages required to fully discharge the battery dependent on the predetermined temperature and materials comprising the lithium ion battery provided.
- 13. The method of claim 10 wherein the negative electrode includes a negative current collector, wherein the step of slowly discharging the lithium ion battery includes discharging the battery to a voltage sufficiently high so as to prevent dissolving the negative current collector.
- 14. A method for reconditioning a lithium ion battery having reduced capacity, comprising the steps of:

providing a power source;

providing a lithium ion battery including a carbonaceous negative electrode having a current collector, a nickel oxide-based positive electrode having a current collector, a nonconductive separator disposed between the negative electrode and the positive electrode, and a source of lithium and an electrolytic solution hermetically sealed in a container, and further including a negative terminal connected to the negative electrode and a positive terminal connected to the positive electrode extending through a face of the container to provide external connections;

connecting the power source to the negative terminal and the positive terminal of the battery;

slowly discharging the lithium ion battery to a predetermined voltage limit sufficiently high so as not to damage the battery cells and at a rate sufficiently low to redistribute lithium ions at the negative electrode while substantially completely discharging the battery; and providing power to the battery from the power source to recharge the lithium ion battery so as to uniformly redistribute the lithium ions in the positive electrode;

wherein the capacity of the battery is restored.

- 15. The method of claim 14 wherein the step of providing a lithium ion battery includes providing a battery having an electrolytic solution comprising LiPF<sub>6</sub>, phosphor hexachloride and organic carbonate.
- 16. The method of claim 14 wherein the step of slowly discharging the lithium ion battery further includes the step of reducing the capacity of the battery in stages to C/n until the predetermined voltage limit is reached.
- 17. The method of claim 16 wherein the step of reducing the capacity of the battery is performed by discharging the battery in a plurality of stages.
- 18. The method of claim 17 wherein the plurality of stages is performed at a predetermined temperature, a number of stages in the plurality of stages required to substantially fully discharge the battery dependent on the predetermined temperature.
- 19. The method of claim 18 wherein the battery is fully discharged at the predetermined temperature of about 20° C at a capacity of C/8096, where C is the rated capacity of the battery.
- 20. The method of claim 18 wherein the battery is fully discharged at the predetermined temperature of about 40° C. at a capacity of about C/1024 where C is the rated capacity of the battery.
- 21. The method of claim 14 wherein the predetermined voltage is in the range of about 2.0 volts to about 2.7 volts.
- 22. The method of claim 17 wherein the battery is discharged in each stage to a value of C/n, where n is a value of about 2<sup>x</sup>, and x corresponds to the stage, up to a thirteenth stage wherein the battery is fully discharged..
- 23. A reconditioned battery lithium ion comprising:

a carbonaceous negative electrode having a current collector;

- a metal oxide-based positive electrode having a surface and that includes a current collector;
- a nonconductive separator disposed between the negative electrode and the positive electrode;
  - a source of lithium;

and an electrolytic solution hermetically sealed in a container;

the battery further including a negative terminal connected to the negative electrode and a positive terminal connected to the positive electrode extending through a face of the container to provide external connections; and

wherein the reconditioned battery is characterized by a substantially uniform distribution of lithium over the surface of the positive electrode after substantially fully discharging the battery followed by recharging the battery.